

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : D21H 19/36, C09J 7/02, B32B 27/20	A1	(11) International Publication Number: WO 00/34580
		(43) International Publication Date: 15 June 2000 (15.06.00)

(21) International Application Number: PCT/US99/29090

(22) International Filing Date: 8 December 1999 (08.12.99)

(30) Priority Data:
09/208,159 9 December 1998 (09.12.98) US

(71) Applicant: FLEXCON COMPANY, INC. [US/US]; 1 Flexcon Industrial Park, Spencer, MA 01562-2642 (US).

(72) Inventors: CASEY, James, M.; 9 Gay Road, Brookfield, MA 01506 (US). KITCH, David, A.; 44 Stafford Street, Apt. 47, Charlton, MA 01507 (US). BECKER, John, M.; 10210 Cambridge Drive, Mokena, IL 60448 (US).

(74) Agents: GAUTHIER, Maurice, E., et al.; Samuels, Gauthier & Stevens LLP, 225 Franklin Street, Suite 3300, Boston, MA 02110 (US).

(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published*With international search report.**Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.*

(54) Title: RELEASE LINERS FOR PRESSURE SENSITIVE ADHESIVE LABELS

(57) Abstract

A release liner (32) for use with face stocks for pressure sensitive labels, tapes, decals and other products formed from sheet and roll stock. A filled polymer (12) is laminated to one side of a paper web (14). An extrudate (24) is laminated to the other side of the paper substrate (14) to form a release liner (32). The filled polymer (12) has paper-like properties and replaces paper tissue back liners.

UNIQUEMENT A TITRE D'INFORMATION

Codes utilisés pour identifier les Etats parties au PCT, sur les pages de couverture des brochures publiant des demandes internationales en vertu du PCT.

AL	Albanie	ES	Espagne	LS	Lesotho	SI	Slovénie
AM	Arménie	FI	Finlande	LT	Lituanie	SK	Slovaquie
AT	Autriche	FR	France	LU	Luxembourg	SN	Sénégal
AU	Australie	GA	Gabon	LV	Lettonie	SZ	Swaziland
AZ	Azerbaïdjan	GB	Royaume-Uni	MC	Monaco	TD	Tchad
BA	Bosnie-Herzégovine	GE	Géorgie	MD	République de Moldova	TG	Togo
BB	Barbade	GH	Ghana	MG	Madagascar	TJ	Tadjikistan
BE	Belgique	GN	Guinée	MK	Ex-République yougoslave de Macédoine	TM	Turkménistan
BF	Burkina Faso	GR	Grèce	ML	Mali	TR	Turquie
BG	Bulgarie	HU	Hongrie	MN	Mongolie	TT	Trinité-et-Tobago
BJ	Bénin	IE	Irlande	MR	Mauritanie	UA	Ukraine
BR	Brésil	IL	Israël	MW	Malawi	UG	Ouganda
BY	Bélarus	IS	Islande	MX	Mexique	US	Etats-Unis d'Amérique
CA	Canada	IT	Italie	NE	Niger	UZ	Ouzbékistan
CF	République centrafricaine	JP	Japon	NL	Pays-Bas	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norvège	YU	Yougoslavie
CH	Suisse	KG	Kirghizistan	NZ	Nouvelle-Zélande	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	République populaire démocratique de Corée	PL	Pologne		
CM	Cameroun	KR	République de Corée	PT	Portugal		
CN	Chine	KZ	Kazakstan	RO	Roumanie		
CU	Cuba	LC	Sainte-Lucie	RU	Fédération de Russie		
CZ	République tchèque	LJ	Licchtenstein	SD	Soudan		
DE	Allemagne	LK	Sri Lanka	SE	Suède		
DK	Danemark	LR	Libéria	SG	Singapour		
EE	Estonie						

RELEASE LINERS FOR PRESSURE SENSITIVE ADHESIVE LABELS

5

FIELD OF THE INVENTION

Release liners for pressure sensitive adhesive labels.

BACKGROUND AND BRIEF SUMMARY OF THE INVENTION

In the manufacture of pressure sensitive adhesive labels, particularly electronically
10 imaged sheet labels, various types of siliconized release liners are used. Most of the
siliconized release liners use a bleached super-calendered or clay-coated Kraft paper. For
"shelf marker" or "shelf talker" sheet labels, a polycoated paper tissue-back release liner
is used.

The paper tissue-back liner provides the desired properties of roughness,
15 coefficients of static and kinetic friction, blocking resistance and moisture barrier to enable
the labels to be stacked and fed into a printer such as a laser printer. The coefficients of
static and kinetic friction, which are partially a result of the roughness, primarily facilitate
the transfer of a label through the printer. The blocking resistance, also partially a result
of the roughness, primarily ensures that the liner-backed labels remain stacked without
20 displacing themselves one to the other, while easily releasing themselves one from the
other, when being removed from the stack and fed to the printer. The moisture barrier
property of the paper tissue-back liner ensures that the liner-backed labels remain
dimensionally stable. However, in an environment of high humidity, the paper tissue
absorbs water vapor and the liner tends to upcurl. In an environment of low humidity the
25 paper tissue disorbs water vapor and the liner tends to down curl.

There are several drawbacks to the use of the paper tissue-back liner. The
machines for electronically printing labels cannot usually handle labels greater than 10.5
to 11 mils in thickness. The use of the paper tissue in combination with the other layers
of the label, results in the label approaching the maximum design thickness that the printer
30 can handle which is not desirable because of the potential for jamming the printer. The
paper tissue in a non-laminated state is fragile and difficult to handle. In order to produce
the tissue backed liner, a base paper is extrusion coated with a nonfilled polymer, typically
LDPE. The tissue is laminated to the polymer at the extrusion nip, while the polymer is

still molten. Once the polymer cools, the tissue is permanently bonded to the base paper. The non-coated side of the base paper is then extrusion coated with another polymeric layer, which polymeric layer is then silicone coated, usually in a separate operation.

Laminating the tissue to the polymer requires a separate unwind operation for the tissue, which increases waste and reduces productivity. Expertise is required in achieving the proper machine tension settings to laminate the tissue without wrinkles. Because the tissue is so fragile, breaks in the tissue are common, leading to machine down time and waste. Any defects in the tissue can lead to the entire liner being unacceptable. Additionally, the paper tissue itself is a relative costly component of the final label.

One object of the present invention is to replace the paper tissue-back release liner with a less expensive yet equally effective release liner.

Another object of the invention is to form the release liner on line.

Still another object of the invention is to provide a release liner which generally can be used as sheet liner or roll liner.

With the present invention, the prior art paper tissue is replaced by a filled polymer which provides several advantages. There is a reduction in the thickness of the final label because the single layer of filled polymer is thinner than the tissue paper/polymer composite. The filled polymer is less costly than the paper tissue and the filled polymer can be extrusion coated and processed on-line in the formation of a release liner.

The filled polymer has certain paper-like properties substantially similar to the properties of the paper tissue. The paper-like properties of the filled polymer are determined primarily by the properties of roughness, blocking resistance and coefficients of static and kinetic friction. The filled polymer also functions as a moisture barrier which dimensionally stabilizes the release liner and the final label. The filled polymer does not absorb and desorb water vapor in environments of high and low humidity and therefore, the release liner of the invention is not susceptible to curling.

Broadly the invention comprises a filled paper-like olefinic resin base layer extrusion coated onto one side of a paper substrate to form a synthetic paper-like laminate release liner base.

In a preferred embodiment of the invention, polyethylene extrusion resins are loaded with filler material in a range of 10-65% by weight, preferably 15 to 40% by

weight based on the total weight of the final filled polyethylene resin.

In a particularly preferred embodiment, an olefinic extrudate is laminated to the other side of the paper substrate to form a release liner.

In another embodiment of the invention the release liner is characterized by a release film coated on the extrudate.

In still another embodiment of the invention, pressure sensitive adhesive is coated onto the release film.

In still another embodiment of the invention, a face stock is adhered to the pressure sensitive adhesive to form a label.

Also within the scope of the invention is the method of manufacture of the release liner in its various alternative embodiments as just described.

BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is a flow diagram of a process embodying the invention;

Fig. 2 is a sectional view of a laminate release liner base;

Fig. 3 is a sectional view of a release liner;

Fig. 4 is a sectional view of the release liner of Fig. 3 coated with a release film;

Fig. 5 is a sectional view of a release liner of Fig. 4 coated with a layer of pressure sensitive adhesive; and

Fig. 6 is a sectional view of a label.

DESCRIPTION OF THE PREFERRED EMBODIMENT(S)

In the present invention a paper web is used as a substrate or intermediate laminae to provide dimensional stability to the release liner. One side of the paper web is

extrusion coated with a filled polymeric material which itself has paper-like characteristics and has at least the roughness, blocking resistance and coefficients of static and kinetic

friction properties which make the release liner especially suitable for use as a sheet liner for sheet stock. The other side of the paper substrate is extrusion coated with an

extrudate, e.g. polyethylene. The extrudate is coated with a release film forming a coated release liner. The coated release liner is combined with a layer of pressure sensitive adhesive and face stock to form a label.

Although the preferred embodiment is described in reference to the use of medium

density extrusion coating grade polyethylene for the base layer and low density extrusion coating grade polyethylene for the extrudate, other polymers or copolymers may be employed, such as polypropylene, polyethylene terephthalate, acrylonitrile, butadiene, styrene, nylon, polystyrene and other appropriate extrudable thermoplastics. Preferred
5 polymers include polypropylene, high density polyethylene, medium density polyethylene, low density polyethylene, high molecular weight HDPE, linear low density polyethylene, straight chained or branched or blends thereof. Further the polymer or copolymer used may be the same or different for the base layer and the extrudate. The polymers can range in density from 0.85 to 1.40, preferably from 0.90-0.95 (g/cc) and have a melt index from
10 1.0-20 (g/10min.). The polymers can be extruded in a thickness between 0.4 to 1.6 mils preferably 0.7-1.2 mils.

The polymer used for base layer is loaded with filler material forming a filled polymer. Preferably the filled polymer is pelletized. Alternatively, the filler can be mixed in the charge of polymer (film forming resin) which is fed to an extrusion orifice
15 associated with the formation of the base layer. The extruded filled polymer has paper-like properties. The outer, exposed, surface should have a roughness of between about 10 to 400 Sheffield units, preferably between about 150 to 350 Sheffield units, exhibit blocking resistance and have coefficients of static and kinetic friction each between about 0.1 to 0.6. These values are determined by the TAPPI standards set forth in the examples
20 that follow.

The filler used is preferably loaded in the polymer in an amount of 15-40% by weight based on the total weight of the filled polymer. Preferred fillers are inert particulates, either organic or inorganic, having an average size of less than 50 microns.

The particulates may be spherical or any non-spherical configuration. As loaded into the
25 polymer the particulates can be uniform in size, non-uniform in size or any combination of sizes. Preferred particulates include glass beads and/or calcium based products.

However other particulates believed to be suitable include clay, silica, mica, talc and titanium dioxide.

The ratio of filler to polymer is selected to ensure that the proper roughness,
30 blocking resistance and coefficients of static and kinetic friction properties are achieved.

The surface of the base layer can be roughened by the mechanical effect of the filler material, the matte finish on the roll which contacts the surface or a combination of both.

To impart other properties to the filled polymer, additives may be incorporated therein. If antistatic properties are desired, commercially available additives can be used.

These additives include but are not limited to quaternary ammonium salts, including sulfate compounds, e.g. Cyastat LS, Cytec Industries (3-Lauramidopropyl) triethylammonium methyl sulfate; chloride compounds, e.g. Arquad 18-50 and Arquad T, Armour Industry Chemical); glycerol monostearates, e.g. Atmer 129, ICI Americas and Pationic 901, Patco American Ingredients; and amides, e.g. lauric diethanolamides and ethoxylated amines.

The release film is preferably a silicone chemistry or other low surface energy polymer (i.e., Fluorocarbon) from which the pressure sensitive adhesive has a relatively low bond (peel force). Commercially available release chemistries include condensation or free radical cured polymers from solvent, solventless, emulsion and radiation cured (UV/EB) systems.

Pressure sensitive adhesives typically used for label stock applications are based on acrylic, vinyl acrylic polymers, multiple polymers or tackified synthetic and natural rubber polymers. The adhesives must possess peel, tack and shear characteristics consistent with converting, dispensing and end use application requirements. Examples of such pressure sensitive adhesives commercially available from FLEXcon, Spencer MA include FLEXcon V-38, V-68 and V-183.

Face stocks suitable for pressure sensitive film label applications include synthetic films based on polymers selected from the group consisting of polyvinyl chloride, polyesters, and filled olefinic resins e.g., polypropylenes and/or polyethylenes. The thicknesses of the face stock can range from 1.0-8.0 mils but are typically in the range of 1.5-4.0 mils. As is well known in the art these films can incorporate fillers and additives to impart physical or functional characteristics such as heat resistance, opacity, flexibility or gloss control.

There are many alternatives in the manufacturing process for pressure sensitive adhesive labels. The release film of the release liner may be coated with a layer of pressure sensitive adhesive for subsequent transfer of the pressure sensitive adhesive to the face stock with which the liner is adhered. When the face stock is combined with the liner, the adhesive is joined to the face stock. Later the liner is removed to expose the adhesive which now remains permanently joined to the face stock. The pressure sensitive

adhesive can be first coated on the face stock and subsequently joined to the release liner.

The base layer and/or extrudate may pass from the extrusion die through a nip formed by chilled finishing rolls, polysteel rolls, silicone rubber rolls or combinations thereof. Either or both sides of the base layer and extrudate may be given a matte or gloss finish if desired.

It will be understood that the steps in the operation of the invention, as shown in Figs. 3-6, can be effected at the same or different facilities by the same or different manufacturers.

Face stock which is formed into labels is usually wound and unwound in roll form and is therefore known as roll stock and the liner is called roll liner. Face stock is also cut into sheets and stacked and is referred to as sheet stock and sheet liner. The invention applies, to roll stock, roll liner, sheet stock and sheet liner. Materials and procedures used for sheet stock and sheet liner maybe the same and/or may differ to some degree for those used for roll stock and roll liner but the principals of construction in manufacture of the release liner of the invention can be similar whether it be liner for roll stock or sheet stock.

Example 1

Referring to Fig. 1 a medium density polyethylene extrusion grade polymer (0.93-0.95 g/cc) having 25% by weight filler loading, specifically 25-50 micron diameter silicon/calcium glass beads, was charged to an extruder 10. The medium density polyethylene is formed by blending high density polyethylene (0.947-0.953 g/cc) with a low density polyethylene (0.907-0.928 g/cc) in a ratio of 2:1 by weight, HDPE/LDPE.

A filled polymeric base layer 12 was extruded at a temperature of about 600°F and a thickness of one mil. A paper substrate 14, International Paper-Bastrop's 70# grade 0612 Reel Cote paper was nipped to the base layer 12 by a matte chill roll 16, 70°F, and a drive roll 18 at a pressure of about 100 psi. Both surfaces of the paper 14 had previously been chemically treated with an aqueous solution of polyethyleneimine to improve the adhesion properties of the surfaces of the paper 14. The laminated base film 12 and paper 14 formed a laminate release liner base 20. The release liner base 20 was reversed at 22 and an extrudate 24 of low density polyethylene extrusion grade polymer and having a thickness of about 1 mil from the extruder 26 was laminated to the release liner base 20

by rollers 28 and 30 at a pressure of about 100 psi to form a release liner 32.

A coater 34 applied a silicone release film 36 to the release liner 32.

Example 2

5 A release liner 32 was produced under the process conditions described for Example 1 except that the layer 12 was loaded, 25% by weight, with a combination of glass beads as described above and dolomite particles (calcium based agglomerates average 5 micron diameter) in a ratio of 50/50 by weight.

The roughness of the base layer 12, based on TAPPI T-538 om-96, 1996, for
10 Examples 1 and 2 was 295 and 290 Sheffield units respectively.

There was no blocking exhibited by the base layer 12, for Examples 1 and 2, based on TAPPI UM-565, 1991.

The coefficients of static and kinetic friction based on TAPPI T-549 pm-90, 1990, were for Example 1 static 0.19 and kinetic 0.18 and for Example 2 static 0.16 and kinetic
15 0.19.

Referring to Figs. 1, 5 and 6, label stock was made from the release liner 32 of Examples 1 and 2. A coater 38 applied a pressure sensitive adhesive 40, FLEXcon's V-38, to the coated release liner 32. Then polyvinyl chloride face stock 42, coated with a laser receptive primer to improve toner fusion, was laminated to the adhesive 40 to form
20 label stock 42. This type of primed face stock is well known to those skilled in the art.

The label stock was fed through a Lexmark 4039 laser printer without difficulty.

Alternatively the pressure sensitive adhesive 40 can be applied to the face stock 42 in a separate step and then the face stock 42 with pressure sensitive adhesive 40 is adhered to the release film 36.

25 The foregoing description has been limited to a specific embodiment of the invention. It will be apparent, however, that variations and modifications can be made to the invention, with the attainment of some or all of the advantages of the invention.

Therefore, it is the object of the appended claims to cover all such variations and modifications as come within the true spirit and scope of the invention.

30 Having described our invention, what we now claim is:

CLAIMS

1 1. A composite release liner for use with label face stock, said release liner
2 comprising:
3 a paper substrate having first and second sides; and
4 a paper-like polymer base layer extrusion coated onto the first side of said paper
5 substrate, the polymer of said base layer being selected from the group consisting of
6 polypropylene, high density polyethylene, medium density polyethylene, low density
7 polyethylene, high molecular weight HDPE, linear low density polyethylene, and straight
8 chained or branched or blends thereof, said paper-like polymer base layer containing filler
9 material and having an exposed surface with a roughness of between about 10 to 400
10 Sheffield units and with coefficients of static and kinetic friction of between about 0.1 to
11 0.6.

1 2. The composite release liner component of claim 1, wherein the paper-like
2 polymer base layer includes a polymer having a density of between about 0.85 to 1.40
3 (g/cc).

1 3. The composite release liner component of claim 1, wherein the paper-like
2 polymer base layer includes a polymer having a density of between about 0.90 to 0.95
3 (g/cc).

1 4. The composite release liner component of claim 1, wherein the paper-like
2 polymer base layer includes a medium density polyethylene having a density of between
3 about 0.93-0.95 (g/cc).

1 5. The composite release liner component of claim 1, wherein the paper-like
2 polymer base layer includes a polymer having a melt index between about 1.0 to 20
3 (g/10min.).

1 6. The composite release liner component of claim 1, wherein the paper-like
2 polymer base layer is extruded to a thickness of between 0.4 to 1.6 mils.

1 7. The composite release liner component of claim 1, wherein the paper-like
2 polymer base layer is extruded to a thickness of between 0.7 to 1.2 mils.

1 8. The composite release liner component of claim 1, having between about
2 15 to 40% by weight of the filler material in the paper-like polymer base layer based on
3 the total weight of the base layer.

1 9. The composite release liner component of claim 1, wherein said filler
2 material is an inert particulate material having average size of less than about 50 microns.

1 10. The composite release liner component of claim 1, wherein said filler
2 material is selected from the group consisting of glass beads, calcium based products, clay,
3 silica, mica, talc, and titanium dioxide.

1 11. The composite release liner component of claim 1, wherein the exposed
2 surface of the paper-like polymer base layer does not exhibit blocking.

1 12. The composite release liner component of claim 1, wherein the exposed surface of
2 the paper-like polymer base layer is characterized by coefficients of static and kinetic
3 friction of between about 0.1 to 0.6.

1 13. The composite release liner component of claim 1, wherein said roughness
2 is between about 150 to 350 Sheffield units.

1 14. The composite release liner component of claim 1, further comprising a
2 polymeric second layer extruded onto the second side of said paper substrate.

1 15. The composite release liner component of claim 14, wherein said polymeric
2 second layer is selected from the group consisting of polypropylene, polyethylene
3 terephthalate, high density polyethylene, medium density polyethylene, low density
4 polyethylene, acrylonitrile, butadiene, styrene, nylon and polystyrene.

1 16. The composite release liner component of claim 14, wherein said polymeric
2 second layer is selected from the group consisting of polypropylene, high density
3 polyethylene, medium density polyethylene, low density polyethylene, acrylonitrile,
4 butadiene, styrene, nylon and polystyrene.

1 17. The composite release liner component of claim 14, wherein said polymeric
2 second layer is selected from the group consisting of polypropylene, high density
3 polyethylene, medium density polyethylene and low density polyethylene.

1 18. The composite release liner component of claim 14, further comprising:
2 a release film on the outer surface of said polymeric second layer.


1 19. The composite release liner component of claim 18, wherein said release
2 film is a silicone-based film.

1 20. The composite release liner component of claim 18, further comprising:
2 a pressure sensitive adhesive adhered to the release film.

1 21. The composite release liner component of claim 20, wherein the pressure
2 sensitive adhesive is selected from the group consisting of acrylics, vinyl acrylics,
3 tackified synthetic and natural rubber polymers.

1 22. The composite release liner component of claim 18, further comprising:
2 a label face stock laminated to said pressure sensitive adhesive.

1 23. The composite release liner component of claim 22, wherein the label face
2 stock is selected from the group consisting of polyvinyl chloride, polyester, polypropylene
3 and/or polyethylene polymers.



9.515

Fig. 5

Fig. A

Fig. 3

F14.2

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/US 99/29090

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 D21H19/36 C09J7/02 B32B27/20

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 D21H C09J B32B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 4 713 273 A (FREEDMAN MELVIN S) 15 December 1987 (1987-12-15) the whole document	1,6,8, 10,11, 18-23
A	US 5 516 393 A (FREEDMAN MELVIN S) 14 May 1996 (1996-05-14) the whole document	1,6,8, 10,11, 14-23
A	US 4 358 494 A (AKIMOTO SABURO ET AL) 9 November 1982 (1982-11-09) the whole document	1,12
A	US 4 956 232 A (BALLONI RICARDO ET AL) 11 September 1990 (1990-09-11) the whole document	1,12
	-/-	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

12 May 2000

Date of mailing of the international search report

25/05/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Nestby, K

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 99/29090

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 516 563 A (SCHUMANN DETLEF E ET AL) 14 May 1996 (1996-05-14) the whole document	1,8-12, 15-17
A	"Paper Vocabulary" 1980, SIS, STOCKHOLM, SWEDEN XP002137567 term 327 ("dimensional stability of paper or board") on page 105	1

INTERNATIONAL SEARCH REPORT

information on patent family members

International Application No

PCT/US 99/29090

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4713273 A	15-12-1987	CA 1325321 A	21-12-1993
		CA 1339836 A	28-04-1998
		US 5372669 A	13-12-1994
		US 4888075 A	19-12-1989
		US 5700564 A	23-12-1997
		US 5985075 A	16-11-1999
		US 6040027 A	21-03-2000
		AU 626962 B	13-08-1992
		AU 4770790 A	03-05-1990
		AU 599586 B	26-07-1990
		AU 5452086 A	26-08-1986
		BR 8605009 A	05-05-1987
		DE 3650593 D	20-02-1997
		DE 3650593 T	11-09-1997
		DE 3679943 D	01-08-1991
		EP 0210261 A	04-02-1987
		EP 0335425 A	04-10-1989
		EP 0681913 A	15-11-1995
		FI 864004 A,B,	03-10-1986
		FI 93186 B	30-11-1994
		JP 2859140 B	17-02-1999
		JP 7324181 A	12-12-1995
		JP 7323493 A	12-12-1995
		JP 7323494 A	12-12-1995
		JP 7323495 A	12-12-1995
		JP 2596923 B	02-04-1997
		JP 62501637 T	02-07-1987
		WO 8604547 A	14-08-1986
		US 4946532 A	07-08-1990
		US 5143570 A	01-09-1992
US 5516393 A	14-05-1996	NONE	
US 4358494 A	09-11-1982	JP 1152202 C	30-06-1983
		JP 55084381 A	25-06-1980
		JP 57045791 B	29-09-1982
US 4956232 A	11-09-1990	CA 2010927 A	26-08-1991
		EP 0444339 A	04-09-1991
		ES 2118712 T	01-10-1998
		GR 3027791 T	30-11-1998
US 5516563 A	14-05-1996	DE 4311422 A	13-10-1994
		EP 0619183 A	12-10-1994
		ZA 9402349 A	17-11-1994



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification⁷ : D21H 19/36, C09J 7/02, B32B 27/20	A1	(11) International Publication Number: WO 00/34580 (43) International Publication Date: 15 June 2000 (15.06.00)
(21) International Application Number: PCT/US99/29090 (22) International Filing Date: 8 December 1999 (08.12.99) (30) Priority Data: 09/208,159 9 December 1998 (09.12.98) US (71) Applicant: FLEXCON COMPANY, INC. [US/US]; 1 Flexcon Industrial Park, Spencer, MA 01562-2642 (US). (72) Inventors: CASEY, James, M.; 9 Gay Road, Brookfield, MA 01506 (US). KITCH, David, A.; 44 Stafford Street, Apt. 47, Charlton, MA 01507 (US). BECKER, John, M.; 10210 Cambridge Drive, Mokena, IL 60448 (US). (74) Agents: GAUTHIER, Maurice, E., et al.; Samuels, Gauthier & Stevens LLP, 225 Franklin Street, Suite 3300, Boston, MA 02110 (US).	(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>	
(54) Title: RELEASE LINERS FOR PRESSURE SENSITIVE ADHESIVE LABELS (57) Abstract <p>A release liner (32) for use with face stocks for pressure sensitive labels, tapes, decals and other products formed from sheet and roll stock. A filled polymer (12) is laminated to one side of a paper web (14). An extrudate (24) is laminated to the other side of the paper substrate (14) to form a release liner (32). The filled polymer (12) has paper-like properties and replaces paper tissue back liners.</p>		

UNIQUEMENT A TITRE D'INFORMATION

Codes utilisés pour identifier les Etats parties au PCT, sur les pages de couverture des brochures publiant des demandes internationales en vertu du PCT:

AL	Albanie	ES	Espagne	LS	Lesotho	SI	Slovénie
AM	Arménie	FI	Finlande	LT	Lituanie	SK	Slovaquie
AT	Autriche	FR	France	LU	Luxembourg	SN	Sénégal
AU	Australie	GA	Gabon	LV	Lettonie	SZ	Swaziland
AZ	Azerbaïdjan	GB	Royaume-Uni	MC	Monaco	TD	Tchad
BA	Bosnie-Herzégovine	GE	Géorgie	MD	République de Moldova	TG	Togo
BB	Barbade	GH	Ghana	MG	Madagascar	TJ	Tadjikistan
BE	Belgique	GN	Guinée	MK	Ex-République yougoslave de Macédoine	TM	Turkménistan
BF	Burkina Faso	GR	Grèce	ML	Mali	TR	Turquie
BG	Bulgarie	HU	Hongrie	MN	Mongolie	TT	Trinité-et-Tobago
BJ	Bénin	IE	Irlande	MR	Mauritanie	UA	Ukraine
BR	Brésil	IL	Israël	MW	Malawi	UG	Ouganda
BY	Bélarus	IS	Islande	MX	Mexique	US	Etats-Unis d'Amérique
CA	Canada	IT	Italie	NE	Niger	UZ	Ouzbékistan
CF	République centrafricaine	JP	Japon	NL	Pays-Bas	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norvège	YU	Yougoslavie
CH	Suisse	KG	Kirghizistan	NZ	Nouvelle-Zélande	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	République populaire démocratique de Corée	PL	Pologne		
CM	Cameroun	KR	République de Corée	PT	Portugal		
CN	Chine	KZ	Kazakhstan	RO	Roumanie		
CU	Cuba	LC	Sainte-Lucie	RU	Fédération de Russie		
CZ	République tchèque	LI	Liechtenstein	SD	Soudan		
DE	Allemagne	LK	Sri Lanka	SE	Suède		
DK	Danemark	LR	Libéria	SG	Singapour		
EE	Estonie						

RELEASE LINERS FOR PRESSURE SENSITIVE ADHESIVE LABELS

5

FIELD OF THE INVENTION

Release liners for pressure sensitive adhesive labels.

BACKGROUND AND BRIEF SUMMARY OF THE INVENTION

10 In the manufacture of pressure sensitive adhesive labels, particularly electronically imaged sheet labels, various types of siliconized release liners are used. Most of the siliconized release liners use a bleached super-calendered or clay-coated Kraft paper. For "shelf marker" or "shelf talker" sheet labels, a polycoated paper tissue-back release liner is used.

The paper tissue-back liner provides the desired properties of roughness, 15 coefficients of static and kinetic friction, blocking resistance and moisture barrier to enable the labels to be stacked and fed into a printer such as a laser printer. The coefficients of static and kinetic friction, which are partially a result of the roughness, primarily facilitate the transfer of a label through the printer. The blocking resistance, also partially a result of the roughness, primarily ensures that the liner-backed labels remain stacked without 20 displacing themselves one to the other, while easily releasing themselves one from the other, when being removed from the stack and fed to the printer. The moisture barrier property of the paper tissue-back liner ensures that the liner-backed labels remain dimensionally stable. However, in an environment of high humidity, the paper tissue absorbs water vapor and the liner tends to upcurl. In an environment of low humidity the 25 paper tissue disorbs water vapor and the liner tends to down curl.

There are several drawbacks to the use of the paper tissue-back liner. The machines for electronically printing labels cannot usually handle labels greater than 10.5 to 11 mils in thickness. The use of the paper tissue in combination with the other layers of the label, results in the label approaching the maximum design thickness that the printer 30 can handle which is not desirable because of the potential for jamming the printer. The paper tissue in a non-laminated state is fragile and difficult to handle. In order to produce the tissue backed liner, a base paper is extrusion coated with a nonfilled polymer, typically LDPE. The tissue is laminated to the polymer at the extrusion nip, while the polymer is

still molten. Once the polymer cools, the tissue is permanently bonded to the base paper. The non-coated side of the base paper is then extrusion coated with another polymeric layer, which polymeric layer is then silicone coated, usually in a separate operation.

Laminating the tissue to the polymer requires a separate unwind operation for the tissue, which increases waste and reduces productivity. Expertise is required in achieving the proper machine tension settings to laminate the tissue without wrinkles. Because the tissue is so fragile, breaks in the tissue are common, leading to machine down time and waste. Any defects in the tissue can lead to the entire liner being unacceptable. Additionally, the paper tissue itself is a relative costly component of the final label.

One object of the present invention is to replace the paper tissue-back release liner with a less expensive yet equally effective release liner.

Another object of the invention is to form the release liner on line.

Still another object of the invention is to provide a release liner which generally can be used as sheet liner or roll liner.

With the present invention, the prior art paper tissue is replaced by a filled polymer which provides several advantages. There is a reduction in the thickness of the final label because the single layer of filled polymer is thinner than the tissue paper/polymer composite. The filled polymer is less costly than the paper tissue and the filled polymer can be extrusion coated and processed on-line in the formation of a release liner.

The filled polymer has certain paper-like properties substantially similar to the properties of the paper tissue. The paper-like properties of the filled polymer are determined primarily by the properties of roughness, blocking resistance and coefficients of static and kinetic friction. The filled polymer also functions as a moisture barrier which dimensionally stabilizes the release liner and the final label. The filled polymer does not absorb and desorb water vapor in environments of high and low humidity and therefore, the release liner of the invention is not susceptible to curling.

Broadly the invention comprises a filled paper-like olefinic resin base layer extrusion coated onto one side of a paper substrate to form a synthetic paper-like laminate release liner base.

In a preferred embodiment of the invention, polyethylene extrusion resins are loaded with filler material in a range of 10-65% by weight, preferably 15 to 40% by

weight based on the total weight of the final filled polyethylene resin.

In a particularly preferred embodiment, an olefinic extrudate is laminated to the other side of the paper substrate to form a release liner.

In another embodiment of the invention the release liner is characterized by a release film coated on the extrudate.

In still another embodiment of the invention, pressure sensitive adhesive is coated onto the release film.

In still another embodiment of the invention, a face stock is adhered to the pressure sensitive adhesive to form a label.

Also within the scope of the invention is the method of manufacture of the release liner in its various alternative embodiments as just described.

BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is a flow diagram of a process embodying the invention;

Fig. 2 is a sectional view of a laminate release liner base;

Fig. 3 is a sectional view of a release liner;

Fig. 4 is a sectional view of the release liner of Fig. 3 coated with a release film;

Fig. 5 is a sectional view of a release liner of Fig. 4 coated with a layer of pressure sensitive adhesive; and

Fig. 6 is a sectional view of a label.

DESCRIPTION OF THE PREFERRED EMBODIMENT(S)

In the present invention a paper web is used as a substrate or intermediate laminae to provide dimensional stability to the release liner. One side of the paper web is extrusion coated with a filled polymeric material which itself has paper-like characteristics and has at least the roughness, blocking resistance and coefficients of static and kinetic friction properties which make the release liner especially suitable for use as a sheet liner for sheet stock. The other side of the paper substrate is extrusion coated with an extrudate, e.g. polyethylene. The extrudate is coated with a release film forming a coated release liner. The coated release liner is combined with a layer of pressure sensitive adhesive and face stock to form a label.

Although the preferred embodiment is described in reference to the use of medium

density extrusion coating grade polyethylene for the base layer and low density extrusion coating grade polyethylene for the extrudate, other polymers or copolymers may be employed, such as polypropylene, polyethylene terephthalate, acrylonitrile, butadiene, styrene, nylon, polystyrene and other appropriate extrudable thermoplastics. Preferred polymers include polypropylene, high density polyethylene, medium density polyethylene, low density polyethylene, high molecular weight HDPE, linear low density polyethylene, straight chained or branched or blends thereof. Further the polymer or copolymer used may be the same or different for the base layer and the extrudate. The polymers can range in density from 0.85 to 1.40, preferably from 0.90-0.95 (g/cc) and have a melt index from 1.0-20 (g/10min.). The polymers can be extruded in a thickness between 0.4 to 1.6 mils preferably 0.7-1.2 mils.

The polymer used for base layer is loaded with filler material forming a filled polymer. Preferably the filled polymer is pelletized. Alternatively, the filler can be mixed in the charge of polymer (film forming resin) which is fed to an extrusion orifice associated with the formation of the base layer. The extruded filled polymer has paper-like properties. The outer, exposed, surface should have a roughness of between about 10 to 400 Sheffield units, preferably between about 150 to 350 Sheffield units, exhibit blocking resistance and have coefficients of static and kinetic friction each between about 0.1 to 0.6. These values are determined by the TAPPI standards set forth in the examples that follow.

The filler used is preferably loaded in the polymer in an amount of 15-40% by weight based on the total weight of the filled polymer. Preferred fillers are inert particulates, either organic or inorganic, having an average size of less than 50 microns.

The particulates may be spherical or any non-spherical configuration. As loaded into the polymer the particulates can be uniform in size, non-uniform in size or any combination of sizes. Preferred particulates include glass beads and/or calcium based products. However other particulates believed to be suitable include clay, silica, mica, talc and titanium dioxide.

The ratio of filler to polymer is selected to ensure that the proper roughness, blocking resistance and coefficients of static and kinetic friction properties are achieved.

The surface of the base layer can be roughened by the mechanical effect of the filler material, the matte finish on the roll which contacts the surface or a combination of both.

To impart other properties to the filled polymer, additives may be incorporated therein. If antistatic properties are desired, commercially available additives can be used.

These additives include but are not limited to quaternary ammonium salts, including sulfate compounds, e.g. Cyastat LS, Cytec Industries (3-Lauramidopropyl)

- 5 triethylammonium methyl sulfate; chloride compounds, e.g. Arquad 18-50 and Arquad T, Armour Industry Chemical); glycerol monostearates, e.g. Atmer 129, ICI Americas and Pationic 901, Patco American Ingredients; and amides, e.g. lauric diethanolamides and ethoxylated amines.

- 10 The release film is preferably a silicone chemistry or other low surface energy polymer (i.e., Fluorocarbon) from which the pressure sensitive adhesive has a relatively low bond (peel force). Commercially available release chemistries include condensation or free radical cured polymers from solvent, solventless, emulsion and radiation cured (UV/EB) systems.

- 15 Pressure sensitive adhesives typically used for label stock applications are based on acrylic, vinyl acrylic polymers, multiple polymers or tackified synthetic and natural rubber polymers. The adhesives must possess peel, tack and shear characteristics consistent with converting, dispensing and end use application requirements. Examples of such pressure sensitive adhesives commercially available from FLEXcon, Spencer MA include FLEXcon V-38, V-68 and V-183.

- 20 Face stocks suitable for pressure sensitive film label applications include synthetic films based on polymers selected from the group consisting of polyvinyl chloride, polyesters, and filled olefinic resins e.g., polypropylenes and/or polyethylenes. The thicknesses of the face stock can range from 1.0-8.0 mils but are typically in the range of 1.5-4.0 mils. As is well known in the art these films can incorporate fillers and additives
25 to impart physical or functional characteristics such as heat resistance, opacity, flexibility or gloss control.

- There are many alternatives in the manufacturing process for pressure sensitive adhesive labels. The release film of the release liner may be coated with a layer of pressure sensitive adhesive for subsequent transfer of the pressure sensitive adhesive to
30 the face stock with which the liner is adhered. When the face stock is combined with the liner, the adhesive is joined to the face stock. Later the liner is removed to expose the adhesive which now remains permanently joined to the face stock. The pressure sensitive

adhesive can be first coated on the face stock and subsequently joined to the release liner.

The base layer and/or extrudate may pass from the extrusion die through a nip formed by chilled finishing rolls, polysteel rolls, silicone rubber rolls or combinations thereof. Either or both sides of the base layer and extrudate may be given a matte or gloss finish if desired.

It will be understood that the steps in the operation of the invention, as shown in Figs. 3-6, can be effected at the same or different facilities by the same or different manufacturers.

Face stock which is formed into labels is usually wound and unwound in roll form and is therefore known as roll stock and the liner is called roll liner. Face stock is also cut into sheets and stacked and is referred to as sheet stock and sheet liner. The invention applies, to roll stock, roll liner, sheet stock and sheet liner. Materials and procedures used for sheet stock and sheet liner maybe the same and/or may differ to some degree for those used for roll stock and roll liner but the principals of construction in manufacture of the release liner of the invention can be similar whether it be liner for roll stock or sheet stock.

Example 1:

Referring to Fig. 1 a medium density polyethylene extrusion grade polymer (0.93-0.95 g/cc) having 25% by weight filler loading, specifically 25-50 micron diameter silicon/calcium glass beads, was charged to an extruder 10. The medium density polyethylene is formed by blending high density polyethylene (0.947-0.953 g/cc) with a low density polyethylene (0.907-0.928 g/cc) in a ratio of 2:1 by weight, HDPE/LDPE.

A filled polymeric base layer 12 was extruded at a temperature of about 600°F and a thickness of one mil. A paper substrate 14, International Paper-Bastrop's 70# grade 0612 Reel Cote paper was nipped to the base layer 12 by a matte chill roll 16, 70°F, and a drive roll 18 at a pressure of about 100 psi. Both surfaces of the paper 14 had previously been chemically treated with an aqueous solution of polyethyleneimine to improve the adhesion properties of the surfaces of the paper 14. The laminated base film 12 and paper 14 formed a laminate release liner base 20. The release liner base 20 was reversed at 22 and an extrudate 24 of low density polyethylene extrusion grade polymer and having a thickness of about 1 mil from the extruder 26 was laminated to the release liner base 20

by rollers 28 and 30 at a pressure of about 100 psi to form a release liner 32.

A coater 34 applied a silicone release film 36 to the release liner 32.

Example 2

5 A release liner 32 was produced under the process conditions described for Example 1 except that the layer 12 was loaded, 25% by weight, with a combination of glass beads as described above and dolomite particles (calcium based agglomerates average 5 micron diameter) in a ratio of 50/50 by weight.

10 The roughness of the base layer 12, based on TAPPI T-538 om-96, 1996, for Examples 1 and 2 was 295 and 290 Sheffield units respectively.

There was no blocking exhibited by the base layer 12, for Examples 1 and 2, based on TAPPI UM-565, 1991.

15 The coefficients of static and kinetic friction based on TAPPI T-549 pm-90, 1990, were for Example 1 static 0.19 and kinetic 0.18 and for Example 2 static 0.16 and kinetic 0.19.

Referring to Figs. 1, 5 and 6, label stock was made from the release liner 32 of Examples 1 and 2. A coater 38 applied a pressure sensitive adhesive 40, FLEXcon's V-38, to the coated release liner 32. Then polyvinyl chloride face stock 42, coated with a laser receptive primer to improve toner fusion, was laminated to the adhesive 40 to form
20 label stock 42. This type of primed face stock is well known to those skilled in the art. The label stock was fed through a Lexmark 4039 laser printer without difficulty.

Alternatively the pressure sensitive adhesive 40 can be applied to the face stock 42 in a separate step and then the face stock 42 with pressure sensitive adhesive 40 is adhered to the release film 36.

25 The foregoing description has been limited to a specific embodiment of the invention. It will be apparent, however, that variations and modifications can be made to the invention, with the attainment of some or all of the advantages of the invention. Therefore, it is the object of the appended claims to cover all such variations and modifications as come within the true spirit and scope of the invention.

30 Having described our invention, what we now claim is:

CLAIMS

1 1. A composite release liner for use with label face stock, said release liner
2 comprising:
3 a paper substrate having first and second sides; and
4 a paper-like polymer base layer extrusion coated onto the first side of said paper
5 substrate, the polymer of said base layer being selected from the group consisting of
6 polypropylene, high density polyethylene, medium density polyethylene, low density
7 polyethylene, high molecular weight HDPE, linear low density polyethylene, and straight
8 chained or branched or blends thereof, said paper-like polymer base layer containing filler
9 material and having an exposed surface with a roughness of between about 10 to 400
10 Sheffield units and with coefficients of static and kinetic friction of between about 0.1 to
11 0.6.

1 2. The composite release liner component of claim 1, wherein the paper-like
2 polymer base layer includes a polymer having a density of between about 0.85 to 1.40
3 (g/cc).

1 3. The composite release liner component of claim 1, wherein the paper-like
2 polymer base layer includes a polymer having a density of between about 0.90 to 0.95
3 (g/cc).

1 4. The composite release liner component of claim 1, wherein the paper-like
2 polymer base layer includes a medium density polyethylene having a density of between
3 about 0.93-0.95 (g/cc).

1 5. The composite release liner component of claim 1, wherein the paper-like
2 polymer base layer includes a polymer having a melt index between about 1.0 to 20
3 (g/10min.).

1 6. The composite release liner component of claim 1, wherein the paper-like
2 polymer base layer is extruded to a thickness of between 0.4 to 1.6 mils.

1 7. The composite release liner component of claim 1, wherein the paper-like
2 polymer base layer is extruded to a thickness of between 0.7 to 1.2 mils.

1 8. The composite release liner component of claim 1, having between about
2 15 to 40% by weight of the filler material in the paper-like polymer base layer based on
3 the total weight of the base layer.

1 9. The composite release liner component of claim 1, wherein said filler
2 material is an inert particulate material having average size of less than about 50 microns.

1 10. The composite release liner component of claim 1, wherein said filler
2 material is selected from the group consisting of glass beads, calcium based products, clay,
3 silica, mica, talc, and titanium dioxide.

1 11. The composite release liner component of claim 1, wherein the exposed
2 surface of the paper-like polymer base layer does not exhibit blocking.

1 12. The composite release liner component of claim 1, wherein the exposed surface of
2 the paper-like polymer base layer is characterized by coefficients of static and kinetic
3 friction of between about 0.1 to 0.6.

1 13. The composite release liner component of claim 1, wherein said roughness
2 is between about 150 to 350 Sheffield units.

1 14. The composite release liner component of claim 1, further comprising a
2 polymeric second layer extruded onto the second side of said paper substrate.

1 15. The composite release liner component of claim 14, wherein said polymeric
2 second layer is selected from the group consisting of polypropylene, polyethylene
3 terephthalate, high density polyethylene, medium density polyethylene, low density
4 polyethylene, acrylonitrile, butadiene, styrene, nylon and polystyrene.

1 16. The composite release liner component of claim 14, wherein said polymeric
2 second layer is selected from the group consisting of polypropylene, high density
3 polyethylene, medium density polyethylene, low density polyethylene, acrylonitrile,
4 butadiene, styrene, nylon and polystyrene.

1 17. The composite release liner component of claim 14, wherein said polymeric
2 second layer is selected from the group consisting of polypropylene, high density
3 polyethylene, medium density polyethylene and low density polyethylene.

1 18. The composite release liner component of claim 14, further comprising:
2 a release film on the outer surface of said polymeric second layer.

1 19. The composite release liner component of claim 18, wherein said release
2 film is a silicone-based film.

1 20. The composite release liner component of claim 18, further comprising:
2 a pressure sensitive adhesive adhered to the release film.

1 21. The composite release liner component of claim 20, wherein the pressure
2 sensitive adhesive is selected from the group consisting of acrylics, vinyl acrylics,
3 tackified synthetic and natural rubber polymers.

1 22. The composite release liner component of claim 18, further comprising:
2 a label face stock laminated to said pressure sensitive adhesive.

1 23. The composite release liner component of claim 22, wherein the label face
2 stock is selected from the group consisting of polyvinyl chloride, polyester, polypropylene
3 and/or polyethylene polymers.




FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 99/29090

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7- D21H19/36 C09J7/02 B32B27/20

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 D21H C09J B32B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 4 713 273 A (FREEDMAN MELVIN S) 15 December 1987 (1987-12-15) the whole document	1,6,8, 10,11, 18-23
A	US 5 516 393 A (FREEDMAN MELVIN S) 14 May 1996 (1996-05-14) the whole document	1,6,8, 10,11, 14-23
A	US 4 358 494 A (AKIMOTO SABURO ET AL) 9 November 1982 (1982-11-09) the whole document	1,12
A	US 4 956 232 A (BALLONI RICARDO ET AL) 11 September 1990 (1990-09-11) the whole document	1,12
-/-		

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- *&* document member of the same patent family

Date of the actual completion of the international search

12 May 2000

Date of mailing of the international search report

25/05/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl.
Fax: (+31-70) 340-3016

Authorized officer

Nestby, K

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 99/29090

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 516 563 A (SCHUMANN DETLEF E ET AL) 14 May 1996 (1996-05-14) the whole document	1,8-12, 15-17
A	"Paper Vocabulary" 1980, SIS, STOCKHOLM, SWEDEN XP002137567 term 327 ("dimensional stability of paper or board") on page 105	1

INTERNATIONAL SEARCH REPORT

information on patent family members

International Application No

PCT/US 99/29090

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4713273 A	15-12-1987	CA 1325321 A	21-12-1993
		CA 1339836 A	28-04-1998
		US 5372669 A	13-12-1994
		US 4888075 A	19-12-1989
		US 5700564 A	23-12-1997
		US 5985075 A	16-11-1999
		US 6040027 A	21-03-2000
		AU 626962 B	13-08-1992
		AU 4770790 A	03-05-1990
		AU 599586 B	26-07-1990
		AU 5452086 A	26-08-1986
		BR 8605009 A	05-05-1987
		DE 3650593 D	20-02-1997
		DE 3650593 T	11-09-1997
		DE 3679943 D	01-08-1991
		EP 0210261 A	04-02-1987
		EP 0335425 A	04-10-1989
		EP 0681913 A	15-11-1995
		FI 864004 A,B,	03-10-1986
		FI 93186 B	30-11-1994
		JP 2859140 B	17-02-1999
		JP 7324181 A	12-12-1995
		JP 7323493 A	12-12-1995
		JP 7323494 A	12-12-1995
		JP 7323495 A	12-12-1995
		JP 2596923 B	02-04-1997
		JP 62501637 T	02-07-1987
		WO 8604547 A	14-08-1986
		US 4946532 A	07-08-1990
		US 5143570 A	01-09-1992
US 5516393 A	14-05-1996	NONE	
US 4358494 A	09-11-1982	JP 1152202 C	30-06-1983
		JP 55084381 A	25-06-1980
		JP 57045791 B	29-09-1982
US 4956232 A	11-09-1990	CA 2010927 A	26-08-1991
		EP 0444339 A	04-09-1991
		ES 2118712 T	01-10-1998
		GR 3027791 T	30-11-1998
US 5516563 A	14-05-1996	DE 4311422 A	13-10-1994
		EP 0619183 A	12-10-1994
		ZA 9402349 A	17-11-1994